



IV1

PVC/NBR/CR, CLOSED CELL FOAM, IN ROLL FORM



Armacell LLC (Conover, NC Plant) manufactures a black, continuous, (rolls / sheets) closed cell, 3.0 - 5.0 lb/ft³ (48 - 80 kg/m³) density, PVC / NBR / CR rubber product Ensolite[®] IV1, that meets all the physical property requirements of ASTM D 1056-14 2A1 / 2C1.

- Has good resistance to oil and fuel.
- Manufactured with nonstaining oils and anti-oxidants.
- Meets the horizontal burn / flame requirements of FMVSS-302 at most thicknesses.
- Listed to UL94 HF-1 at 0.051" (1.3 mm) and UL94 V-0 at 0.460" (11.7 mm) and higher (UL File# QMFZ2.E55798).
- Listed with UL to UL50E [periodic and continuous compression] (UL File# JMST2.MH10189).
- Listed on the approved source list for Chrysler MSAY 516 Type 1.

- UL 94 V-0, V-1 and HF-1 listed for flame
- UL 50E (periodic and continuous compression) listed for gaskets and seals
- ASTM D 1056-14 2A1 / 2C1 grade product
- ASTM D 6576-13 Type II, Grades A and B, Condition Soft material
- PVC / NBR / CR closed cell rubber material manufactured in continuous rolls



Engineered For Success.

Roll Size Information:

Gauge (in)	Gauge (fraction of an inch)	Gauge (mm)	Tolerance (in)	Tolerance (mm)	Roll Size Options		Roll Size Options		Comments
					W (in)	L (ft)	W (m)	L (m)	
0.375	3/8	9.53	0.328 - 0.422	8.33 - 10.72	72	90	1.83	27.43	S1S
0.500	1/2	12.70	0.500 - 0.700	12.70 - 17.78	54	150	1.37	45.72	S1S
0.750	3/4	19.05	0.750 - 0.950	19.05 - 24.13	60	200	1.52	60.96	S2S
0.750	3/4	19.05	0.670 - 0.830	17.02 - 21.09	72	90	1.83	27.43	S2S
1.000	1	25.40	1.000 - 1.200	25.40 - 30.48	48	8	1.22	2.44	S2S - Sheet
1.000	1	25.40	1.000 - 1.200	25.40 - 30.48	54	75	1.37	22.86	S2S
1.250	1-1/4	31.75	1.250 - 1.450	31.75 - 36.83	54	50	1.37	15.24	S2S
1.250	1-1/4	31.75	1.250 - 1.450	31.75 - 36.83	54	50	1.37	15.24	S2S
1.250	1-1/4	31.75	1.250 - 1.450	31.75 - 36.83	54	100	1.37	30.48	S2S
1.500	1-1/2	38.10	1.500 - 1.700	38.10 - 43.18	54	50	1.37	15.24	S2S
1.500	1-1/2	38.10	1.500 - 1.700	38.10 - 43.18	54	100	1.37	30.48	S2S

S1S = Skin 1 side

S2S = Skin 2 sides

NS = No splice

L = Additional lengths available

Automotive and Industrial Specifications:

The following is a list of automotive and industrial specifications that Armacell Ensolite® IV1 has been tested to or can meet. Additional specifications are listed that have a few exceptions. Feel free to suggest other automotive, military or industrial specifications, and a full review will be made.

Source	Specification	Armacell Ensolite® IV1	Comments
ASTM	ASTM D1056-14	2A1 / 2C1	Additional (optional) suffixes can be added
ASTM	ASTM G21	Data available	Fungus resistance test method. Note: IV1 does not incorporate an added biocide.
ASTM	ASTM D 1149	Rating 0	Ozone resistance test method
ASTM	ASTM D 6576-13	Type II, Grades A and B, Condition Soft	Formerly MIL-R-6130C
Caterpillar	1E0720	1E0720D Grade 1	Request information regarding exceptions
Chrysler	Chrysler MSZ-75 J18	2A1 / 2C1	Additional (optional) suffixes can be added
Chrysler	Chrysler MS JP9-4	Meets at most thicknesses	Flame resistance (horizontal burn rate)
Chrysler	Chrysler MSAY 516	Type 1	Approved source list
Federal	FMVSS-302	Meets at most thicknesses	Flame resistance (horizontal burn rate). See note 1
Federal	FAR 25.853	Contact Armacell Technical Service Department	12 Second Vertical Burn Test. (Test report available upon request)
Ford	WSK M2D 419-A	Type 2	See note 2
GM	GM 6090-M	(B4A) Meets at most thicknesses	Flame resistance tested per GM 9070-P (horizontal burn rate)
GM	GMW15473	Class I Type IV	CD tested at 50% deflection. See note 3
Gulfstream	GAP105K Rev C	Part Numbers GAP105K14-18	Approved source list
ISO	ISO 6916	2A1 / 2C1	Exception to compression set
Military	ASTM D 6576-13	Type II, Grades A and B, Condition Soft	Formerly MIL-R-6130C
SAE	SAE J18 APR2002	2A1 / 2C1	Additional (optional) suffixes can be added
SAE	SAE J369	Meets at most thicknesses	Flame resistance (horizontal burn rate)
SAE	SAE J 1351	Rating 2	Odor test method
Toyota	TSM 1501G	2A1 / 2C1	Exception to compression set
Toyota	TSM 0500G	Meets at most thicknesses	Flame resistance (horizontal burn rate)
UL	UL94 V-0	V-0 UL Listed at 11.7 mm and higher	Vertical flame resistance specification. (UL file# QMFZ2. E55798)
UL	UL94 HF-1	HF-1 UL Listed at 1.3 mm and higher	Horizontal flame resistance specification. (UL file# QMFZ2. E55798)
UL	UL50	Suitable as gasket material for UL 50 and UL 50E (continuous and periodic compression) enclosures	Request additional information about UL enclosure types. (UL file# JMST2.MH10189)

Note 1: A number of horizontal burn tests can also be listed (GM 6090, BMW, Volvo etc.). Request additional information.

Note 2: For all Ford WSK M2D419A callouts, request full information for each product due to some possible exceptions (example: non-standard staining requirements)

Note 3: For all GMW 15473 callouts, Armacell certifies to the "basic" requirements only. Request additional information for each product. Providing application (interior, exterior or under-hood) and part thickness is helpful.

Data Sheet:

Physical Properties	Unit	Test Method	Typical Result
Density	lb/ft ³	ASTM D 1056	3.0 - 5.0
	kg/m ³	ASTM D 1056	48 - 80
Hardness, Durometer Shore 00		ASTM D 2240	30 - 50
Compression Deflection (25%)	psi	ASTM D 1056	2.0 - 5.0
	kPa	ASTM D 1056	13.8 - 34.5
50% Compression Set (Room temp)	%	ASTM D 1056	40 max
Tensile Strength	psi	ASTM D 412 (Die A)	50 min
	kPa	ASTM D 412 (Die A)	345 min
Tear Strength	lb/in	ASTM D 624 (Die C)	9
	kN/m	ASTM D 624 (Die C)	1.6
Elongation	%	ASTM D 412 (Die A)	100 min
Service Temperature (1)			
Low	°F (°C)	ASTM D 1056	-40 (-40)
High Continuous	°F (°C)		---
High Intermittent (2)	°F (°C)		200 (93.3)
Water Absorption			
Maximum Weight Change	%	ASTM D 1056	10
Fluid Immersion (7 days at 23°C [73.4°F])			
ASTM Ref. Fuel B, Weight Change (%)	%	ASTM D 1056	250 max
Accelerated Aging (7 days at 70°C [158°F])			
Flexibility (180° bend without cracking)			Pass
Appearance change			None
Change in Compression Deflection	%	ASTM D 1056	± 30
Combustion Characteristics (3)		Thicknesses	Comments
FMVSS-302			Pass at most thicknesses
FAR 25.853		Contact Armacell technical service department	
UL94			
V-0		0.461" (11.7 mm) and higher	Listed, UL file# QMFZ2.E55798
HF-1		0.051" (1.3 mm) and higher	Listed, UL file# QMFZ2.E55798

(1) This recommendation is based on polymer type only. For specific application requirements please contact technical service.

(2) This temperature is the maximum allowable for intermittent exposure only. For continuous use temperature please contact technical service.

(3) Flammability – This item and any corresponding data refer to typical performance in the specific test indicated and should not be construed to imply this material's behavior in other fire conditions.

NBR – Acrylonitrile Butadiene Rubber

PVC – Polyvinyl Chloride

CR – Chloroprene (Neoprene)

ASTM D 1056 designation: 2A1 / 2C1

SAE J 18 APR2002 designation: 2A1 / 2C1

ASTM D 6576: Type II, Grades A and B, Condition Soft

UL Listed to UL 50E (UL file# JMST2.MH10189)

IV1 is on the approved source list for Chrysler MSAY 516 (Type 1)

UL File Number for Armacell Ensolite® IV1

UL File Number: QMFZ2.E55798

Plastics – Component (UL 94)

Material Dsg	Color	Min.		H	H	R T I		V	4	C	
		Thk	Flame	W	A	Elec	Mech	T	9	T	
		mm	Class	I	I		Imp	Str	R	5	I
Nitrile Rubber / Polyvinylchloride / Neoprene (NBR / PVC / CR), closed-cell foam, "Ensolite", furnished as profiles, tubes or sheets.											
IV1(n)	BK	1.3	HF-1	-	-	50	-	50	-	-	-
		11.7	V-0	-	-	50	-	50			
		12.5	V-0	-	-	50	-	50			
		12.5	HF-1	-	-	50	-	50			

(n) - Density range 0.063 - 0.074 g/cc w/o skin and 0.077 - 0.156 g/cc w/skin

UL File Number for Armacell Ensolite® IV1

UL File Number: JMST2. MH10189

IV1, IV2, IVC	Closed cellular PVC/NBR/CR gasket material	Types "IV1", "IV2", "IVC". Suitable as a gasket material for UL 50 enclosure types 2, 3, 3R, 3S, 4, 4X, 5, 6, 6P, 12, 12K and 13. [UL50E [Continuous and Periodic Compression]]
UL 50E	Tensile strength and elongation after heat aging 168 h (7 d) at 158°F (70°C)	75% of original for tensile strength 60% of original for elongation
UL 50E	Oil immersion / oil aging (IRM # 903), % volume change after 70 h @ room temperature	Shall not swell more than 25% or shrink more than 1% of original volume
UL 157	Tensile strength and elongation after heat aging 70 h at 212°F (100°C)	60% of original (For both tensile and elongation)

UL Yellow Card Listing Verification On-line

To obtain verification on-line:

1. www.ul.com - THEN
2. Click on "On-Line Certifications Directory" in gray area at bottom of web page - THEN
3. Click on "Company Name" in the general search area - THEN
4. Type in "Armacell" - & click "SEARCH"
5. 14 (fourteen) Armacell file numbers come up (2 for Armacell Germany, 1 for Armacell Middle East, 1 for Armacell Thailand, 1 for Armacell Korea & 1 for Wall & Partition Facings)
6. Click on QMFZ2.E55798 for Armacell (Ensolite®), (ArmaSport®) & (Monarch®) products [Flame/UL94]
7. Click on JMLU2.MH25062 for Armacell (Monarch®) products listed to JMLU2 [Gaskets & Seals]
8. Click on JMST2.MH10189 or JMST2.MH30018 for Armacell (Ensolite®) and or Armacell (Monarch®) products listed to JMST2 [Gasket Materials]
9. Click on OPET2.MQ1977 for Armacell (ArmaSport®) products listed to Lifesaving Equipment, Marine - Component

ARMACELL LLC
TEL: 800.973.0490
FAX: 800.973.0489

info.us@armacell.com
www.armacell.us
55 Vilcom Center Drive Suite 200 Chapel Hill, NC 27514



Armacell provides this information as a technical service. To the extent the information is derived from sources other than Armacell, Armacell is substantially, if not wholly, relying upon the other source(s) to provide accurate information. Information provided as a result of Armacell's own technical analysis and testing is accurate to the extent of our knowledge and ability, as of date of printing, using effective standardized methods and procedures. Each user of these products, or information, should perform their own tests to determine the safety, fitness and suitability of the products, or combination of products, for any foreseeable purposes, applications and uses by the user and by any third party to which the user may convey the products. Since Armacell cannot control the end use of this product, Armacell does not guarantee that the user will obtain the same results as published in this document. The data and information are provided as a technical service and are subject to change without notice.