



**XE-40 Rolls**  
Extruded Crosslinked Polyethylene

Corporate Headquarters:  
1806 Conant St.  
Elkhart, IN 46516



This data sheet property values are typical of the material and are intended to provide guidance to customers; they do not constitute a specification and should not be used for specification development.

[www.worldwidefoam.com](http://www.worldwidefoam.com)

[Info@worldwidefoam.com](mailto:Info@worldwidefoam.com)

PHYSICAL PROPERTIES		TEST METHOD	VALUES	USA UNITS	VALUES	METRIC UNITS
Density - Nominal		ASTM D3575	4	lb/ft <sup>3</sup>	64	kg/m <sup>3</sup>
Tensile Strength		ASTM D3575	102	psi	703	kPa
Tear Strength		ASTM D3575	28	lb/in	500	kg/m
Elongation		ASTM D3575	184	%	184	%
Firmness		ASTM D2240	38	Asker C	38	Asker C
Compressive Stress						
Compression Set	50% 24hr	ASTM D3575 Suffix B	<25	%	<25	%
Compression Strength	25%	ASTM D3575 Suffix D	20	psi	138	kPa
	50%		35		241	
Working Temperature Range		Internal Test	-40 to 225	°F	-40 to 107	°C
Water Absorption 7 Days		ASTM-D1667	0.163	Lbs./sq.ft		
Flammability		FMVSS302	Pass	Pass/Fail	1.63"/min	Burn Rate

For roll size and color availability, please see the color and sizing chart, or contact us at [info@worldwidefoam.com](mailto:info@worldwidefoam.com) or visit [www.worldwidefoam.com](http://www.worldwidefoam.com)

\*Testing done according to ASTM D3575 & ASTM C177 (thermal conductivity) standards.

The data represented on this technical data sheet should be used as a guideline for product selection. This data is not intended to represent, replace or be used as a proxy for a specific product sales specification. The physical properties are averages based on limited production runs and are subject to change as additional data becomes available.