



Worldwide Foam
A Jacobs & Thompson Company

5260

EPDM/CR/SBR

This data sheet property values are typical of the material and are intended to provide guidance to customers; they do not constitute a specification and should not be used for specification development.

Corporate Headquarters:

1806 Conant St.
Elkhart, IN 46516

www.worldwidefoam.com

Info@worldwidefoam.com

Ph: 574-968-8268

Fax: 574-970-0926



Item	Specs	Test Method
Grade	2A2	ASTM D1056-07
Density (PCF) (kg/m ³)	8.13 - 11.88 PCF 130 - 190 kg/m ³	ASTM D1056
Compression Deflection (CFD) (psi) (kPa) @25%	9 - 13 psi 62 - 90 kPa	ASTM D1056
Hardness - Durometer Shore OO	40– 60	ASTM D 2240
Compression Set 25%	30	ASTM D 1056
Tensile Strength (psi)(kPa)	51 psi 350 kPa	ASTM D412
Elongation (%)	80	ASTM D412
Tear Strength (lb/in)(kN/m)	8.6 lb/in 1.5 kN/m	ASTM D624
Flame Resistance	Pass 1.4mm—1.8mm	UL 94HF-1

The data on this technical data sheet should be used as a guideline for product selection. This data is not intended to represent, replace or be used as a proxy for a specific product sales specification. The physical properties are averages based on limited production runs and are subject to change as additional data becomes available.