

Sulphur Free EPDM

This data sheet property values are typical of the material and are intended to provide guidance to customers; they do not constitute a specification and should not be used for specification development.

Corporate Headquarters: 1806 Conant St. Elkhart, IN 46516 www.worldwidefoam.com Info@worldwidefoam.com

> Ph: 574-968-8268 Fax: 574-970-0926

Item	Sp	ecs	Test Method
Grade	2A2/RE42		ASTM D1056
Density (PCF) (kg/m³)	6.2 - 8.7 PCF		ISO 845-88
	100 - 140 kg/m³		AS
Compression Deflection (CFD) (psi) (kPa) @25%	5 psi @25% 10 psi @50% 35 kPa @25% 70 kPa @50%		ASTM D 1056/85
Shore Hardness OO (Durometer)	45 - 55		ASTM D2240
Compression Set %	12% @ 25% 18% @ 50%		ASTM D395
Tensile Strength (psi)(kPa)	65.2 psi		ASTM D412
	450 kPa		
Elongation (%)	>150%		ASTM D412
Tear Strength Resistance (lb/in)	16		ASTM D624
Water Absorption by Weight %	0.13		ASTM D1056
Accelerated Age Testing:	<5%		ASTM D1204
7 Days @ 158 °F Change in CFD			
Service Temperature (°F)(°C)	$^{\circ}\mathrm{F}$	$^{\circ}\mathrm{C}$	ASTM 3575
Low High High intermittent	-40 203	-40 95	
Flame Resistance	Pass		FMVSS-302-S4.3
Industry and OEM Specifications: Jacobs and Thompson Inc. certifies that the following product meets the required specifications;	WSK-M2D-419-A Type 3 FMVSS 302 VW 50180 TSM 1501G 2A2		

The data on this technical data sheet should be used as a guideline for product selection. This data is not intended to represent, replace or be used as a proxy for a specific product sales specification. The physical properties are averages based on limited production runs and are subject to change as additional data becomes available.