



**SEKISUI 5782U**  
Low VOC Acrylic Adhesive

This data sheet property values are typical of the material and are intended to provide guidance to customers; they do not constitute a specification and should not be used for specification development.

Corporate Headquarters:  
1806 Conant St.  
Elkhart, IN 46516

[www.worldwidefoam.com](http://www.worldwidefoam.com)

[Info@worldwidefoam.com](mailto:Info@worldwidefoam.com)

Ph: 574-968-8268 Fax: 574-970-0926



**Typical Physical Properties**

PHYSICAL PROPERTIES	VALUES	TEST METHODS
Adhesive Thickness	0.013 mm	
Adhesion / SS	21.8 N/25mm	JIS Z0237
Adhesion / SS	16.6 N/25mm	JIS Z0237
Adhesion / PP	13.8 N/25mm	JIS Z0237
Adhesive / PE	7.4 N/25mm	JIS Z0237
Holding performance @ 40°C	1.0mm	JIS Z0237

Resistant to water, detergent and alcohol. Not recommended for use in contact with aliphatic or aromatic hydrocarbons.

The data represented on this technical data sheet should be used as a guideline for product selection. This data is not intended to represent, replace or be used as a proxy for a specific product sales specification. The physical properties are averages based on limited production runs and are subject to change as additional data becomes available.