



EV-20D

2 Stage Crosslinked Polyethylene
With EVA (Ethylene Vinyl Acetate)

This data sheet property values are typical of the material and are intended to provide guidance to customers; they do not constitute a specification and should not be used for specification development.

Corporate Headquarters:

1806 Conant St.

Elkhart, IN 46516

www.worldwidefoam.com

Info@worldwidefoam.com

Ph: 574-968-8268 Fax: 574-970-0926

PHYSICAL PROPERTIES		TEST METHOD	VALUES	USA UNITS	VALUES	METRIC UNITS
Density - Nominal		ASTM D3575	2	lb/ft ³	32.04	kg/m ³
Tensile Strength		ASTM D3575	50	psi	345	kPa
Tear Strength		ASTM D3575	11	lb/in	196	kg/m
Elongation		ASTM D3575	290	%	290	%
Firmness		ASTM D2240	23	Asker C	23	Asker C
Compressive Stress						
Compression Set	50% 24hr	ASTM D3575 Suffix B	<18	%	<18	%
Compression Strength	25%	ASTM D3575 Suffix D	9	psi	62	kPa
	50%		17		117	
Working Temperature Range		Internal Test	-40 to 220	°F	-40 to 107	°C
Water Absorption 7 Days		ASTM-D1667	0.0123	Lbs./sq.ft		
Flammability		FMVSS 302	Pass at 0.25", burn rate: 3.06"/min			

For bun size and color availability, please see the color and sizing chart, or contact us at info@worldwidefoam.com or visit www.worldwidefoam.com

*Testing done according to ASTM D3575 & ASTM C177 (thermal conductivity) standards.

The data on this technical data sheet should be used as a guideline for product selection. This data is not intended to represent, replace or be used as a proxy for a specific product sales specification. The physical properties are averages based on limited production runs and are subject to change as additional data becomes available.