



**1120**

ECH

This data sheet property values are typical of the material and are intended to provide guidance to customers; they do not constitute a specification and should not be used for specification development.

Corporate Headquarters:

1806 Conant St.  
Elkhart, IN 46516

www.worldwidefoam.com

[Info@worldwidefoam.com](mailto:Info@worldwidefoam.com)

Ph: 574-968-8268

Fax: 574-970-0926



Item	Specs		Test Method
Grade	2B1		ASTM D1056
	2B1		SAE J-18 APR2002
Density (PCF) (kg/m <sup>3</sup> )	12 – 18 PCF 192 – 288 kg/m <sup>3</sup>		ASTM D 3676
Compression Deflection @25% (CFD)(psi) (kPa)	2 – 5 psi 13.7 kpa – 34.4 kPa		ASTM D 1056
Shore Hardness OO (Durometer)	50 – 60		ASTM D 2240
Compression Set @25%	≤ 25		ASTM D 1056
Tensile Strength (psi) (kPa)	120 psi 827 kPa		ASTM D 412 (Die A)
Elongation %	250		ASTM D 412 (Die A)
Tear Strength Resistance (ppi)	18		ASTM D 412 (Die C)
Water Absorption by Weight %	<5		ASTM D 1056
Accelerated Age Testing Oven Aged 7 Days @ 158 °F Change in CFD (%)	± 30%		ASTM D 1056
Service Temperature (°F)(°C)	°F	°C	ASTM D 746
- Low	-40	- 40	
- High Continuous	300	148	
- High Intermittent	325	162	
Flame Resistance	Pass		FMVSS 302
Industry and OEM Specifications: Jacobs and Thompson Inc. certifies that the following product meets the required specifications;	MS-AY432 GMW15473 CLASS 1 TYPE 5 ASTM D 1056-14 2B1 GM 6086M Type IIIA; ASTM D 1056-14 2B1		

The data on this technical data sheet should be used as a guideline for product selection. This data is not intended to represent, replace or be used as a proxy for a specific product sales specification. The physical properties are averages based on limited production runs and are subject to change as additional data becomes available.