



1220

Neoprene/EPDM/SBR Blend

This data sheet property values are typical of the material and are intended to provide guidance to customers; they do not constitute a specification and should not be used for specification development.

Corporate Headquarters:

1806 Conant St.
Elkhart, IN 46516

www.worldwidefoam.com

Info@worldwidefoam.com

Ph: 574-968-8268

Fax: 574-970-0926



Item	Specs		Test Method
Grade	2A1		ASTM D1056-07
Density (PCF) (kg/m ³)	4 – 8 PCF 64 - 128 kg/m ³		ASTM D 1056
Compression Deflection (CFD) (psi) (kPa) @25%	2 – 5 psi 13.7 – 34.4 kPa		ASTM D1056
Shore Hardness OO (Durometer)	40 - 50		ASTM D1056
Compression Set @50%	≤ 40		ASTM D1056
Tensile Strength (psi)(kPa)	75 psi 517 kPa		ASTM D412
Elongation (%)	125		ASTM D412
Tear Strength Resistance (ppi)	9.6		ASTM D 624
Water Absorption by Weight %	< 10		ASTM D1056
Accelerated Age Testing: 7 Days @ 158 °F Chang in CD	± 30% max		ASTM D1056
Service Temperature (°F)(°C)	°F	°C	ASTM D1056
Low	-40	-40	
High Continuous	200	93	
High intermittent	250	121	
Flame Resistance	Pass @ 3/16" and higher		FMVSS 302
Industry and OEM Specifications: Jacobs and Thompson Inc. certifies that the following product meets the required specifications;	MS-Z-75 2A1 SAE J-18 JUL92 2A1 CSA C22.2 ASTM D1056-14 2A1 MSAY 430 Type 2 WSK M2D 419-A Type 2 GMW15473 Class I Type IV TSM 1501G 2A1		

The data on this technical data sheet should be used as a guideline for product selection. This data is not intended to represent, replace or be used as a proxy for a specific product sales specification. The physical properties are averages based on limited production runs and are subject to change as additional data becomes available.