



XP-30

2 Stage Crosslinked Polyethylene

This data sheet property values are typical of the material and are intended to provide guidance to customers; they do not constitute a specification and should not be used for specification development.

Corporate Headquarters:
1806 Conant St.
Elkhart, IN 46516

www.worldwidefoam.com

Info@worldwidefoam.com

PHYSICAL PROPERTIES		TEST METHOD	VALUES	USA UNITS	VALUES	METRIC UNITS
Density - Nominal		ASTM D3575	3	lb/ft ³	48	kg/m ³
Tensile Strength		ASTM D3575	70	psi	482	kPa
Tear Strength		ASTM D3575	15	lb/in	267	kg/m
Elongation		ASTM D3575	240	%	240	%
Firmness		ASTM D2240	35	Asker C	35	Asker C
Compressive Stress						
Compression Set	50% 24hr	ASTM D3575 Suffix B	<15	%	<15	%
Compression Strength	25%	ASTM D3575 Suffix D	12	psi	83	kPa
	50%		21		145	
Working Temperature Range		Internal Test	-40 to 225	°F	-40 to 107	°C
Water Absorption 7 Days		ASTM-D1667	.0134	lbs./sq.ft		
Flammability		FMVSS302	Pass	Pass/Fail	2.78 in/min	Burn Rate

For bun size and color availability, please see the color and sizing chart, or contact us at info@worldwidefoam.com or visit www.worldwidefoam.com

*Testing done according to ASTM D3575 & ASTM C177 (thermal conductivity) standards.

The data represented on this technical data sheet should be used as a guideline for product selection. This data is not intended to represent, replace or be used as a proxy for a specific product sales specification. The physical properties are averages based on limited production runs and are subject to change as additional data becomes available.